



常州隽隆复合材料有限公司

CHANGZHOU JLON COMPOSITE CO.,LTD

Han Yuan 2-607/608,New North District,Changzhou 213022,Jiangsu,China

Tel:86-519-89810829

Email:info@jloncomposite.com



### Technical Data Sheet

1.常规型号(Normal Type):	JL9-W-2800		
纤维直径 (Filament Diameter)	9		
可燃物含量(%) Loss on ignition	0.5		

#### 2.控制指标(Specification):

NO.	项目	控制指标	检测方法 Method	
	Item	Specification	GB Standard	ISO Standard
1	外观 Appearance	无污染 No Contamination		
2	玻璃类型 Glass Type	E 玻璃 E-Glass	GB/T 1549	
3	浸润剂类型 Size Type	淀粉型 STARCH		
4	单丝纤维直径(μm) Filament Diameter	公称值±1 Nominal Value±1	GB/T 7690.5	ISO1888
5	抗拉强度(N/Tex) Tensile Strength	≥0.05	GB/T 7690.5	ISO3341
6	线密度[tex(g/km)] Roving Density	公称值±5% Nominal Value±5%	GB/T 7690.1	ISO1889
7	可燃物含量(%) Loss on ignition	公称值±0.3 Nominal Value±0.20	GB/T 9914.2	ISO1887
8	含水率%	≤1	GB/T 9914.1	ISO3344

	<b>Moisture content</b>			
9	<b>最佳存储期 Best storage period</b>	The product should be stored in a cool and dry place, the temperature and humidity of the warehouse should be kept at 10°C~35°C, 35%~85%, and the product should be used within 6 months after the date of production.		